

Super plasticizer and a high range water reducer for concrete

DESCRIPTION

HI-CONTECH 07, is a dark colored ready to use super plasticizer based on synthetic polymers with high molecular weight and increased fluidifying power. It accelerates the initial setting time, lowers the w/c ratio and improves the properties of fresh and hardened concrete.

STANDARDS

ASTM C-494 Typ F ; TS EN 934-2

FIELD OF APPLICATION

HI-CONTECH 07 can be used on all types of high quality concrete where high early mechanical strength and significantly lower w/c ratio is need. Due to it's high quality characteristics, HI-CONTECH 07 is particularly indicated for use in concrete mixed on site or ready-mixed concrete transported by mixer trucks where high initial strengths are needed.

ADVANTAGES

HI-CONTECH 07 is a super plasticizer and within a dosage range from 0.8 – 2.0 %, the following can be obtained; Concrete with an improved w/c ratio (water reduction of 20 – 30 %) Waterproofing concrete. • Non segregation, fluid, plastic concrete without bleeding. • Homogeneous and cohesive concrete. • Easily pumped concrete with good workability and with good finishing. Durable and highly impermeable concrete. • Improved properties of fresh and hardened concrete. • Concrete with high initial and final strengths. •

COMPATIBILITY

HI-CONTECH 07 is compatible with the following; All Portland and other types of cement in accordance with ASTM standards. Air entraining admixtures. • EXPAN non shrink agents. • Fly ash. • Polypropylene and steel fibers.

MECHANICAL STRENGTHS

Compared to a concrete without the admixture, the use of HI-CONTECH 07 in concrete will result in an increase in the mechanical strength, in proportion with water reduction, in some cases, by 100%. With the use of HI-CONTECH 07, high initial and ultimate mechanical strengths will be evidenced. Because of the reduction in the water/cement ratio, increased resistance and durability, lower shrinkage and permeability will be obtained.

DOSAGE AND USE

The dosage of HI-CONTECH 07 is 0.8 – 2.0 kg for every 100 kg of cement, to be added in mixer with the last mix water. (after 70% introduction of the mix water) The addition of admixture on dry aggregates and cement is not recommended since it lowers the plasticizing and water reducing effect.

WORKABILITY

Workability time after the use of HI-CONTECH 07 in the concrete depends on the applied dosage, type and dosage of cement and aggregates and ambient temperature. In general, the extended workability time after the addition of the admixture, is about < 90 min. at 20°C The loss of workability is gradual and only practical site tests will specify the workability.

PRECAUTIONS

Use gloves and avoid contact with eyes and skin. Consult a physician if contact with eyes and skin.

PACKING AND STORAGE

HI-CONTECH 07 is available in bulk, 30 kg and 250 kg drums, 1200 kg plastic cubitainers. If stored in between +5 °C / +25 °C in it's original packaging shelf life is more than 1 year.